

NAME	PE/ALU/PE	STRUCTURE	PE/ALU/PE	DATE	2018.2.1
STANDARD		GB/T1004-2008			
TEST ITEMS		TECHNICAL INDICATORS		RESULT	SINGLE CONCLUSION
EXTERIOR		SMOOTH, NO WRINKLE		SMOOTH, NO WRINKLE	PASS
THICKNESS		0.142mm		0.142mm	PASS
GRAMMS (g/m ²)		142		142	PASS
TENSILE	MD	20.8	22.2	25.1	PASS
STRENGTH (N)	TD	26.8	25.7	24.9	PASS
TENSILE ELONGATION (%)	MD	46.9	29	28.2	PASS
	TD	19.8	20.6	18.6	PASS

Insulation products